



AMORPHOUS POWDER CORE SERIES PRODUCTS

PRODUCT CHARACTERISTICS

Features

- Reduce Overall Component Cost than Other Solution
- Low Ripple Current
- High Efficiency
- Smaller in Size (Save PCB Size)
- Smallest Temperature Rise among Powdered Core

Material Information

Properties	APT	MPP	High Flux	Sendust	Ferrite
Saturation Flux Density Bs(G)	15,000	7,500	15,000	10,000	3,000
DC Bias Property @ 100Oe	70%	50%	70%	45%	Gap dep
Core Loss @ 100kHz, 0.1T	600	500	1,300	850	Gap dep

Specification of APT Series

APT	Size(Bare) (OD×ID×HT)	Size(Coated) (OD×ID×HT)	A_L (nH/N ²)	A_c (cm ²)	Le (cm)	SA (cm ²)	Wa (cm ²)	WaAc (cm ⁴)	Vol (cm ³)
APT13PXX	12.7×7.6×4.8	13.5×7.0×5.5	27	0.11	3.12	5.6	0.38	0.04	0.36
APT17PXX	16.5×10.2×6.4	17.4×9.5×7.1	35	0.19	4.11	9.2	0.71	0.14	0.79
APT18PXX	17.3×9.7×6.4	18.0×9.0×7.1	43	0.23	4.14	9.9	0.64	0.13	0.96
APT20PXX	20.3×12.7×6.4	21.1×12.1×7.1	32	0.23	5.09	12.1	1.14	0.26	1.15
APT23PXX	22.9×14.0×7.6	23.6×13.4×8.4	43	0.33	5.67	15.7	1.41	0.47	1.88
APT24PXX	23.6×14.4×8.9	24.3×13.8×9.7	51	0.39	5.88	17.9	1.49	0.58	2.28
APT27PXX	26.9×14.7×11.2	27.7×14.1×12.0	75	0.65	6.35	24.7	1.56	1.02	4.15
APT33PXX	33.0×19.9×10.7	33.8×19.3×11.6	61	0.67	8.15	31.5	2.93	1.97	5.48
APT36PXX	35.8×22.4×10.5	36.7×21.5×11.3	56	0.68	8.98	34.5	3.64	2.47	6.09
APT40PXX	39.9×23.1×14.5	40.7×23.3×15.4	81	1.07	9.84	48.4	4.27	4.58	10.55
APT46PXX	46.7×24.1×18.0	47.6×23.3×18.9	135	1.99	10.74	69.3	4.27	8.50	21.37
APT47PXX	46.7×28.7×15.2	47.6×27.9×16.1	86	1.34	11.63	61.7	6.11	8.19	15.58
APT50PXX	50.8×31.8×13.5	51.7×30.9×14.4	73	1.25	12.73	64.2	7.50	9.38	15.93
APT57PXX	57.2×26.4×15.2	58.0×25.6×16.1	138	2.29	12.51	91.0	5.14	11.77	28.60